

ALEACIÓN 25 / ALEACIÓN DE COBALTO L605

Dynamic Metals es un proveedor de aleación 25 / L605 de cobalto (AMS 5759, AMS 5537) del Reino Unido.
Suministramos metal de alta calidad sin cantidad mínima de pedido para barras, chapas y placas en stock.

Especificación técnica

Especificaciones relacionadas

AMS 5759

AMS 5537

Gravedad específica

9.14 g/cm³

Composición química (WT %)

	Min	Max
C	0.05	0.15
Mn	1	2
Si	-	0.04
P	-	0.04
S	-	0.03
Cr	19	21

Ni	9	11
W	14	16
Fe	-	3
Co	Bal	-

Propiedades mecánicas típicas

Type	Bar (Normalised and tempered, 0.5" and above)	
0.2% Proof Stress	MPA	1276
Tensile Strength	MPA	1517
Elongation	%	10
Reduction of area	%	35
Hardness	HBW	269

Need more information? **Get in touch**

General Enquiries

+44(0) 1525 217 556

Email us here

Head Office

40 Eden Way
Chartwell Business Park
Leighton Buzzard
Bedfordshire
LU7 4FY

T: +44 (0)1525 217 556

Conversion Centre

Suite 2 Meadowhall Riverside
Meadowhall Road
Sheffield
South Yorkshire
S9 1BW

T: +44 (0)1143 030 320

Useful Links

[Privacy Policy](#)

[Sitemap](#)

