

AMS 5737 - A286 ACIER INOXYDABLE BAR

L'A286 (AMS 5737, AMS 5726, AMS 5731, AMS 5732) est un alliage durcissable par précipitation. Sa teneur élevée en nickel et en chrome lui confère une bonne résistance à la corrosion jusqu'à environ 1300 degrés C et une oxydation jusqu'à environ 1500 degrés Fahrenheit. L'A286 peut être durci à un niveau de résistance élevé. L'alliage est également utilisé pour les applications à basse température nécessitant un matériau ductile, non magnétique, à haute résistance, à des températures allant de la température ambiante au dessus de -320 ° F au moins. Cet alliage peut être utilisé pour des applications de corrosion modérée en solution aqueuse.

Specific Gravity													
7.9 g/cm3													
Typical Applications							Related Specifications						
Fasteners							AMS 5726						
Stud Bolts							AMS 5731						
Industrial Gas Turbines							AMS 5732						
							AMS 5737						
							BS HR 51						
							BS HR 52						
							W.Nr 1.4943						
							W.Nr 1.4944						
							UNS S66286						
Chemical Composition (Wt %)													
	C	Mn	P	S	Si	Cr	Ni	Mo	Ti	V	Al	B	Fe
Min	-	-	-	-	-	13.5	24	1	1.9	0.10	-	0.003	-
Max	0.08	2.0	0.025	0.025	1	16	27	1.5	2.35	0.50	0.035	0.010	Bal
Typical Mechanical Properties													
	0.2% Proof Stress	Tensile Strength	Elongation	Reduction of area	Hardness								

	MPA	MPA	%	%	HB
	Min	Min	Min	Min	
Sol treated and Aged 1800 Deg F (AMS 5732)	586	896	15	–	248 – 341
Sol Treated and Aged 1650 Deg F (AMS 5737)	655	965	12	–	277 – 363

* Every effort has been made to ensure that our technical specifications are accurate. However, technical specifications included within Dynamic Metals Ltd should be used as a guideline only and are subject to change without notice.

General Enquiries

T: +44 (0) 1525 217 556 [\(tel:+4401525217556\)](tel:+4401525217556)

E: sales@dynamicmetalsltd.com [\(mailto:sales@dynamicmetalsltd.com\)](mailto:sales@dynamicmetalsltd.com)



UK Address:

Head Office

40 Eden Way
Chartwell Business Park
Leighton Buzzard
Bedfordshire
LU7 4FY

T: +44 (0)1525 217 556 [\(tel:+441525217556\)](tel:+441525217556)

Conversion Centre

Suite 2 Meadowhall Riverside
Meadowhall Road
Sheffield
South Yorkshire
S9 1BW

T: +44 (0)1143 030 320 [\(tel:+4401143030320\)](tel:+4401143030320)

Registered Office (only)

The Granary
Crowhill Farm Ravensden Road
Wilden
Bedfordshire
MK44 2QS

T: +44 (0)1525 217 556 [_ \(tel:+441525217556\)](tel:+441525217556)



[\(/media/zn2dbklo/cyber-essentials-certified-plus.png\)](#)



[\(/media/dyelbliq/cyber-essentials-certified.png\)](#)