

AMS 4944, AMS 4945 - TITANE GRADE 9 TUBES

Le Titane 3AL2.5V ou Titane Grade 9 (AMS 4944, AMS 4945) possède une résistance intermédiaire entre le Titane commercialement pur et le TA6V. Il est généralement utilisé en condition écroui.

Specific Gravity							
4.484 g/cm ³							
Typical Applications				Related Specifications			
Hydraulic Systems				AMS 4944			
Fuel Systems				AMS 4945			
Bicycle Frames				UNS R56320			
Sports Equipment				ASTM B338			
Chemical Composition (Wt %)							
	Al	V	Fe	N	O	C	H
Min	2.5	2.0	–	–	–	–	–
Max	3.5	3.0	0.30	0.02	0.12	0.05	0.0125
Typical Mechanical Properties							
	0.2% Proof Stress	Tensile Strength	Elongation				
	MPA	MPA	%				
	Min	Min	Min				
Ann	515	620	15				
CWSR	725	860	10				
* Every effort has been made to ensure that our technical specifications are accurate. However, technical specifications included within Dynamic Metals Ltd should be used as a guideline only and are subject to change without notice.							

General Enquiries

T: +44 (0) 1525 217 556 [_\(tel:+4401525217556\)](tel:+4401525217556)

E: sales@dynamicmetalsltd.com [_\(mailto:sales@dynamicmetalsltd.com\)](mailto:sales@dynamicmetalsltd.com)



UK Address:

Head Office

40 Eden Way
Chartwell Business Park
Leighton Buzzard
Bedfordshire
LU7 4FY

T: +44 (0)1525 217 556 [_\(tel:+441525217556\)](tel:+441525217556)

Conversion Centre

Suite 2 Meadowhall Riverside
Meadowhall Road
Sheffield
South Yorkshire
S9 1BW

T: +44 (0)1143 030 320 [_\(tel:+4401143030320\)](tel:+4401143030320)

Registered Office (only)

The Granary
Crowhill Farm Ravensden Road
Wilden
Bedfordshire
MK44 2QS

T: +44 (0)1525 217 556 [_\(tel:+441525217556\)](tel:+441525217556)



[\(/media/zn2dbklo/cyber-essentials-certified-plus.png\)](#)



[\(/media/dyelbliq/cyber-essentials-certified.png\)](#)