

## TITANE GRADE 1 TÔLES ET PLAQUES

Le Titane grade 1 possède la résistance mécanique la moins élevée mais la meilleure formabilité des Titanes commercialement pur. De plus, il présente une excellente résistance à la corrosion dans les environnements fortement oxydants et légèrement réducteurs.

Typical Applications		Related Specifications				
Desalination  Plate Frame Heat Exchangers  Dimensionally Stable Anodes  Marine Equipment		ASTM B265				
Chemical Composition (Wt %)						
		C	N	O	Fe	H
	Min	-	-	-	-	-
	Max	0.08	0.03	0.18	0.2	0.015
Typical Mechanical Properties						
0.2% Proof Stress		Tensile Strength	Elongation	Reduction of area		
MPA		MPA	%	%		
Min		Min				
170		240	24	30		
* Every effort has been made to ensure that our technical specifications are accurate. However, technical specifications included within Dynamic Metals Ltd should be used as a guideline only and are subject to change without notice.						

### General Enquiries

T: +44 (0) 1525 217 556 [\(tel:+4401525217556\)](tel:+4401525217556)

E: [sales@dynamicmetalsltd.com](mailto:sales@dynamicmetalsltd.com) [\(mailto:sales@dynamicmetalsltd.com\)](mailto:sales@dynamicmetalsltd.com)



**UK Address:**

*Head Office*

40 Eden Way  
Chartwell Business Park  
Leighton Buzzard  
Bedfordshire  
LU7 4FY

T: +44 (0)1525 217 556 [\\_\(tel:+441525217556\)](tel:+441525217556)

*Conversion Centre*

Suite 2 Meadowhall Riverside  
Meadowhall Road  
Sheffield  
South Yorkshire  
S9 1BW

T: +44 (0)1143 030 320 [\\_\(tel:+4401143030320\)](tel:+4401143030320)

*Registered Office (only)*

The Granary  
Crowhill Farm Ravensden Road  
Wilden  
Bedfordshire  
MK44 2QS

T: +44 (0)1525 217 556 [\\_\(tel:+441525217556\)](tel:+441525217556)



[\(/media/zn2dbklo/cyber-essentials-certified-plus.png\)](#)



[\(/media/dyelbliq/cyber-essentials-certified.png\)](#)