

TITANE GRADE 1 TÔLES ET PLAQUES

Le Titane grade 1 possède la résistance mécanique la moins élevée mais la meilleure formabilité des Titanes commercialement pur. De plus, il présente une excellente résistance à la corrosion dans les environnements fortement oxydants et légèrement réducteurs.

Typical Applications		Related Specifications				
Desalination Plate Frame Heat Exchangers Dimensionally Stable Anodes Marine Equipment		ASTM B265				
Chemical Composition (Wt %)						
		C	N	O	Fe	H
	Min	–	–	–	–	–
	Max	0.08	0.03	0.18	0.2	0.015
Typical Mechanical Properties						
0.2% Proof Stress		Tensile Strength	Elongation	Reduction of area		
MPA		MPA	%	%		
Min		Min				
170		240	24	30		
* Every effort has been made to ensure that our technical specifications are accurate. However, technical specifications included within Dynamic Metals Ltd should be used as a guideline only and are subject to change without notice.						

General Enquiries

T: +44 (0) 1525 217 556 [\(tel:+4401525217556\)](tel:+4401525217556)

E: sales@dynamicmetalsltd.com [\(mailto:sales@dynamicmetalsltd.com\)](mailto:sales@dynamicmetalsltd.com)



UK Address:

Head Office

40 Eden Way
Chartwell Business Park
Leighton Buzzard
Bedfordshire
LU7 4FY

T: +44 (0)1525 217 556 [_\(tel:+441525217556\)](tel:+441525217556)

Conversion Centre

Suite 2 Meadowhall Riverside
Meadowhall Road
Sheffield
South Yorkshire
S9 1BW

T: +44 (0)1143 030 320 [_\(tel:+4401143030320\)](tel:+4401143030320)

Registered Office (only)

The Granary
Crowhill Farm Ravensden Road
Wilden
Bedfordshire
MK44 2QS

T: +44 (0)1525 217 556 [_\(tel:+441525217556\)](tel:+441525217556)



[\(/media/zn2dbklo/cyber-essentials-certified-plus.png\)](#)



[\(/media/dyelbliq/cyber-essentials-certified.png\)](#)