

STOP NIKLU 90

Stop Niklu 90

Stop 90 to utwardzany wydzieleniowo stop odporny na pelzanie, przeznaczony do pracy w temperaturach do 920°C.

Specific Gravity																
8.19 g/cm ³																
Typical Applications								Related Specifications								
Turbine Blades Hot-Working Tools High Temperature Springs								BS 3 HR 2 ASTM B 637								
Chemical Composition (Wt %)																
	Ni	Cr	Fe	C	Mn	Si	Cu	Al	Ti	Co	S	B	Zr	Ag	Bi	Pb
Min		18.0						1.0	2.0	15						
Max		21.0	1.5	0.1	1.0	1.0	0.2	2.0	3.0	21.0	0.015	0.020	0.150	5 ppm	1 ppm	20 ppm
Typical Mechanical Properties																
0.2% Proof Stress												Tensile Strength	Elongation	Hardness		
MPA												MPA	%	HB		
695												1080	20	293		

General Enquiries

T: +44 (0) 1525 217 556 [\(tel:+4401525217556\)](tel:+4401525217556)

E: sales@dynamicmetalsltd.com [\(mailto:sales@dynamicmetalsltd.com\)](mailto:sales@dynamicmetalsltd.com)



UK Address:

Head Office

40 Eden Way
Chartwell Business Park
Leighton Buzzard
Bedfordshire
LU7 4FY

T: +44 (0)1525 217 556 [_\(tel:+441525217556\)](tel:+441525217556)

Conversion Centre

Suite 2 Meadowhall Riverside
Meadowhall Road
Sheffield
South Yorkshire
S9 1BW

T: +44 (0)1143 030 320 [_\(tel:+4401143030320\)](tel:+4401143030320)

Registered Office (only)

The Granary
Crowhill Farm Ravensden Road
Wilden
Bedfordshire
MK44 2QS

T: +44 (0)1525 217 556 [_\(tel:+441525217556\)](tel:+441525217556)



[\(/media/zn2dbklo/cyber-essentials-certified-plus.png\)](/media/zn2dbklo/cyber-essentials-certified-plus.png)



[\(/media/dyelbliq/cyber-essentials-certified.png\)](#)