

## 4130 ALLOY STEEL BARS AND TUBING

4130 (AMS 6360, AMS 6370, AMS 6371, AMS 6348)

is a through hardening low alloy steel containing molybdenum and chromium as strengthening agents. 4130 responds well to nitriding for very good wear and abrasion resistance.

Specific Gravity								
7.8 g/cm <sup>3</sup>								
Typical Applications					Related Specifications			
Aircraft engine mounts Aircraft seating Roll Cages Bicycle frames Well head components					<b>AMS 6360</b> <b>AMS 6370</b> <b>AMS 6371</b> <b>AMS 6348</b> <b>UNS G41300</b> <b>Mil S 6758</b> <b>Mil T 67366</b>			
Chemical Composition (Wt %)								
	C	Mn	P	S	Si	Cr	Ni	Mo
Min	0.28	0.40	–	–	0.15	0.80	–	0.15
Max	0.33	0.60	0.025	0.025	0.35	1.10	0.25	0.25
Typical Mechanical Properties								
	0.2% Proof Stress	Tensile Strength	Elongation	Reduction of area	Hardness			
	MPA	MPA	%	%	HRC			
Tube	482	655	12					
Bar (Hardened and Tempered)	517 (min)	655 (min)	20 (min)	40 (min)	18-22			

\* This data has been supplied in good faith and is indicative only. It has been provided for general information purposes only and is not to be relied upon in place of the full specification. Mechanical properties can vary considerably with different supply conditions such as heat treatment or temper and product dimensions.

No liability will be accepted by Dynamic Metals Ltd in respect of any action taken by any third party in reliance of any of the data provided.

The information provided in this datasheet has been taken from multiple recognised sources. No guarantee is given that the information is from the latest issue of these sources and no guarantee is given that the information in the datasheet is accurate or up to date.

Material supplied by Dynamic Metals Ltd may vary significantly from this data but will conform to the relevant and applicable standards. All transactions are subject to Dynamic Metals Ltd latest Terms and Conditions of Sale.

As the products detailed may be used for a wide variety of purposes and as Dynamic Metals Ltd has no control over their use, Dynamic Metals Ltd specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by Dynamic Metals Ltd to any third party is given for that party's assistance only and without liability on the part of Dynamic Metals Ltd.

All transactions are subject to Dynamic Metals Ltd latest Terms and Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions, a copy of which is available by request or by downloading from our website.

---

## General Enquiries

T: +44 (0) 1525 217 556 [\(tel:+4401525217556\)](tel:+4401525217556)

E: [sales@dynamicmetalsltd.com](mailto:sales@dynamicmetalsltd.com) [\(mailto:sales@dynamicmetalsltd.com\)](mailto:sales@dynamicmetalsltd.com)



## UK Address:

### *Head Office*

40 Eden Way  
Chartwell Business Park  
Leighton Buzzard  
Bedfordshire  
LU7 4FY

T: +44 (0)1525 217 556 [\(tel:+441525217556\)](tel:+441525217556)

### *Conversion Centre*

Suite 2 Meadowhall Riverside  
Meadowhall Road  
Sheffield  
South Yorkshire  
S9 1BW

T: +44 (0)1143 030 320 [\(tel:+4401143030320\)](tel:+4401143030320)

### *Registered Office (only)*

The Granary  
Crowhill Farm Ravensden Road  
Wilden  
Bedfordshire  
MK44 2QS

T: +44 (0)1525 217 556 [\(tel:+441525217556\)](tel:+441525217556)



[\(/media/zn2dbklo/cyber-essentials-certified-plus.png\)](#)



[\(/media/dyelbliq/cyber-essentials-certified.png\)](#)