

# Alloy 188 Cobalt Alloy - AMS 5772

## Typical Applications

- Aerospace
- Gas Turbine Engines

Alloy 188 is known for its superior resistance to corrosion and oxidation at elevated temperatures, this is due to its composition, containing significant quantities of cobalt and chromium. This allows Alloy 188 to be well suited for high temperature environments. The alloy maintains structural integrity when exposed to extreme heat, oxidising agents, and corrosive media that would rapidly degrade many conventional materials.

Cobalt Alloy 188 falls under the category of superalloys - an elite family of metallic composites purpose-engineered to endure extraordinarily hostile operating environments and withstand severe mechanical stresses. Standard alloys would rapidly deteriorate under such punishing conditions, yet this superalloy exhibits remarkable resilience in the face of extraordinarily hostile environments that would compromise ordinary materials. Cobalt Alloy 188 exhibits exceptional resilience where standard materials would simply fail.

The presence of chromium, a key component at roughly 22%, allows a tenacious oxide layer to form on the alloy's surface, this acts as a barrier, which prevents corrosion. Cobalt itself is highly resistant to chloride-induced corrosion, a type of degradation that plagues many other alloys.

Industries that rely on Cobalt Alloy 188 include aviation, where it sees use in aircraft engines and hot section components and in the gas industry where it used in turbine engines.

## Technical specification

### Related Specifications

AMS 5608

AMS 5772

### Specific Gravity

9.14g/cm³

### Chemical Composition (WT %)

	Min	Max
C	0.05	0.15
Mn	-	1.25

<b>Si</b>	0.20	0.50
<b>P</b>	-	0.02
<b>S</b>	-	0.015
<b>Cr</b>	20	24
<b>Ni</b>	20	24
<b>W</b>	13	16
<b>La</b>	0.02	0.12
<b>B</b>	-	0.015
<b>Fe</b>	-	3
<b>Co</b>	-	Bal

*Typical Mechanical Properties*

		Bars
<b>0.2% Proof Stress</b>	MPA	379

<b>Tensile Strength</b>	MPA	862
<b>Elongation</b>	4D	45%
<b>Hardness</b>	HB	302

Need more information? **Get in touch**

---

## General Enquiries

+44(0) 1525 217 556

[Email us here](#)

## Head Office

40 Eden Way  
 Chartwell Business Park  
 Leighton Buzzard  
 Bedfordshire  
 LU7 4FY

T: +44 (0)1525 217 556

## Conversion Centre

Suite 2 Meadowhall Riverside  
 Meadowhall Road  
 Sheffield  
 South Yorkshire  
 S9 1BW

T: +44 (0)1143 030 320

## Useful Links

[Privacy Policy](#)

[Sitemap](#)

