

# Alloy 25 / L605 Cobalt Alloy

## Typical Applications

Aircraft Engines

Gas Turbines

Ball Bearings

Industrial Furnace Lines

*Cobalt Alloy 25/L605 has a carefully balanced composition of cobalt, chromium, tungsten, and other trace elements. The main strengths of this alloy are its ability to resist corrosion and wear, as well as its capacity to endure high temperatures. Cobalt Alloy L605 maintains its structural integrity well, even when subjected to caustic environments, abrasive forces or scorching heat.*

The main strength of Cobalt Alloy L605 is its hardness, which is achieved through a heat treatment process. This hardness is no mere boast - it translates into exceptional wear resistance that allows the alloy to shrug off the harshest conditions. Whether it's being subjected to relentless friction or operating in abrasive environments, L605 exhibits a tenacity that few materials can match. In industries where downtime is unacceptable and failure is not an option, L605 stands as a tireless workhorse, ready to take on the most punishing challenges.

But the capabilities of Cobalt Alloy L605 don't end there. Its remarkable strength at extreme heat levels means it is a good choice for high heat applications, e.g. Industrial Furnace Lines. From the blistering environments of aerospace applications to the furnace-like conditions of power generation and chemical processing plants, components crafted from this alloy stand unwavering, their structural integrity never compromised.

## Technical specification

### *Related Specifications*

**AMS 5759**

**AMS 5537**

### *Specific Gravity*

**9.14 g/cm<sup>3</sup>**

### *Chemical Composition (WT %)*

	Min	Max
<b>C</b>	0.05	0.15
<b>Mn</b>	1	2

<b>Si</b>	-	0.04
<b>P</b>	-	0.04
<b>S</b>	-	0.03
<b>Cr</b>	19	21
<b>Ni</b>	9	11
<b>W</b>	14	16
<b>Fe</b>	-	3
<b>Co</b>	Bal	-

### *Typical Mechanical Properties*

<b>Type</b>		Bar (Normalised and tempered, 0.5" and above)
<b>0.2% Proof Stress</b>	MPA	1276
<b>Tensile Strength</b>	MPA	1517
<b>Elongation</b>	%	10

<b>Reduction of area</b>	%	35
<b>Hardness</b>	HBW	269

*Need more information? **Get in touch***

---

### **General Enquiries**

+44(0) 1525 217 556

[Email us here](#)

### **Head Office**

40 Eden Way  
 Chartwell Business Park  
 Leighton Buzzard  
 Bedfordshire  
 LU7 4FY

T: +44 (0)1525 217 556

### **Conversion Centre**

Suite 2 Meadowhall Riverside  
 Meadowhall Road  
 Sheffield  
 South Yorkshire  
 S9 1BW

T: +44 (0)1143 030 320

### **Useful Links**

[Privacy Policy](#)

[Sitemap](#)

