

AMS 6514 - Maraging 300 Stainless Steel

Typical Applications

Driveshafts

Gears

Fasteners

Landing and Takeoff gear

Missile and ejector systems

Torsion springs



Maraging 300 (also known as Vascomax® 300) is an 18% nickel, cobalt strengthened steel.

It is a very high strength material reaching a UTS of 1930 MPA after heat treatment. It is produced by Vacuum Induction Melting (VIM) followed by Vacuum Arc Remelting (VAR).

Related Products

Maraging 250 Stainless Steel

Maraging 300 Stainless Steel

Maraging 350 Stainless Steel

Technical specification

Related Specifications

AMS 6514

ASTM A538

Mil-S-46850D

UNS K93120

W.Nr 1.6358

Specific Gravity

8.0 g/cm³

Chemical Composition (WT %)

	Min	Max
C	-	0.03
Si	-	0.10
Mn	-	0.10
P	-	0.010
S	-	0.010
Al	0.05	0.15
Co	8.5	9.5
Ni	18.0	19.00
Mo	4.6	5.20
Ti	0.5	0.8
Cr	-	0.5
Cu	-	0.5

Sheffield
South Yorkshire
S9 1BW

T: +44 (0)1143 030 320

Useful Links

[Privacy Policy](#)

[Sitemap](#)

