

## AMS 5596, AMS 5597, NICKEL ALLOY 718 SHEET & PLATE

Alloy 718 (alternatively known by Special Metals trade name Inconel 718) AMS 5596, AMS 5597, is a nickel chromium alloy which can be heat treated to give high strength, good corrosion resistance and is readily fabricated into complex parts with a very good resistance to postweld cracking. Alloy 718 can work effectively between -423 to 1300 deg F.

Specific Gravity															
7.98 g/cm3															
Typical Applications								Related Specifications							
Exhausts Liquid rocket components involving cryogenic temperatures								<b>AMS 5596</b> <b>AMS 5597</b> <b>UNS N07718</b> <b>ASTM B670</b>							
Chemical Composition (Wt %)															
	Ni	Cr	Fe	Mo	Nb+Ta	C	Mn	Si	Ph	S	Ti	Cu	B	Al	Co
Min	50	17	Bal	2.8	4.75	–	–	–	–	–	0.65	–	–	0.20	–
Max	55	21	–	3.3	5.50	0.08	0.035	0.35	0.015	0.015	1.15	0.30	0.006	0.80	1.00
Mechanical Properties in the annealed condition															
											0.2% Proof Stress	Tensile Strength	Elongation		
											MPA	MPA	%		
											Max	Max	Min		
Sheet and strip											550	965	30		
Plate											725	1035	30		
Mechanical Properties in the solution treated and precipitation heat treated condition															

0.2% Proof Stress	Tensile Strength	Elongation
MPA	MPA	%
Min	Min	Min
1035	1240	12

\* This data has been supplied in good faith and is indicative only. It has been provided for general information purposes only and is not to be relied upon in place of the full specification. Mechanical properties can vary considerably with different supply conditions such as heat treatment or temper and product dimensions.

No liability will be accepted by Dynamic Metals Ltd in respect of any action taken by any third party in reliance of any of the data provided.

The information provided in this datasheet has been taken from multiple recognised sources. No guarantee is given that the information is from the latest issue of these sources and no guarantee is given that the information in the datasheet is accurate or up to date.

Material supplied by Dynamic Metals Ltd may vary significantly from this data but will conform to the relevant and applicable standards. All transactions are subject to Dynamic Metals Ltd latest Terms and Conditions of Sale.

As the products detailed may be used for a wide variety of purposes and as Dynamic Metals Ltd has no control over their use, Dynamic Metals Ltd specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by Dynamic Metals Ltd to any third party is given for that party's assistance only and without liability on the part of Dynamic Metals Ltd.

All transactions are subject to Dynamic Metals Ltd latest Terms and Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions, a copy of which is available by request or by downloading from our website.

## General Enquiries

T: +44 (0) 1525 217 556 [\(tel:+4401525217556\)](tel:+4401525217556)

E: [sales@dynamicmetalsltd.com](mailto:sales@dynamicmetalsltd.com) [\(mailto:sales@dynamicmetalsltd.com\)](mailto:sales@dynamicmetalsltd.com)



## UK Address:

### Head Office

40 Eden Way  
 Chartwell Business Park  
 Leighton Buzzard  
 Bedfordshire  
 LU7 4FY

T: +44 (0)1525 217 556 [\(tel:+441525217556\)](tel:+441525217556)

### Conversion Centre

Suite 2 Meadowhall Riverside  
 Meadowhall Road  
 Sheffield  
 South Yorkshire  
 S9 1BW

T: +44 (0)1143 030 320 [\(tel:+4401143030320\)](tel:+4401143030320)

### Registered Office (only)

The Granary  
 Crowhill Farm Ravensden Road

Wilden  
Bedfordshire  
MK44 2QS

T: +44 (0)1525 217 556 [.\(tel:+441525217556\)](tel:+441525217556)



[\(/media/zn2dbklo/cyber-essentials-certified-plus.png\)](#)



[\(/media/dyelbliq/cyber-essentials-certified.png\)](#)