

## AMS 5643, AMS 5604, AMS 5622, 17-4PH STAINLESS STEEL

The 17/4PH is an austenitic stainless steel alloy that has superior resistance to corrosion and outstanding mechanical properties. Conforming to the stringent AMS 5604, AMS 5622, and AMS 5643 specifications, this alloy is meticulously engineered to meet the most demanding industrial requirements.

The exceptional corrosion resistance of the 17/4PH alloy stems from its carefully crafted chemical composition, blending chromium, nickel, and copper in precise proportions, this unique formulation imbues the material with an unrivaled ability to withstand a broad spectrum of corrosive environments.

Moreover, the alloy's precipitation hardening capabilities allow for precise control over its mechanical properties, through a carefully controlled heat treatment process, 17/4PH can achieve remarkable strength and hardness levels while maintaining excellent toughness and ductility.

The remarkable combination of high strength and lightweight characteristics makes the 17/4PH alloy exceptionally well-suited for applications where optimal strength-to-weight ratios are paramount. From aerospace components that demand superior performance without compromising on weight, to oil and gas equipment subjected to harsh environments, and intricately designed precision engineering parts requiring meticulous craftsmanship, this versatile material excels across a wide range of demanding applications.

Specific Gravity											
7.74 g/cm3											
Typical Applications						Related Specifications					
Motor Shafts  Aircraft Structural Parts  Valve Stems  Gears						AMS 5604					
						AMS 5622					
						AMS 5643					
						UNS S17400					
						W.Nr 1.4548					
Chemical Composition (Wt %)											
	C	Si	Mn	P	S	Cr	Mo	Ni	Cb	Cu	Fe
Min	–	–	–	–	–	15.00	–	3.00	5 x %C	3.00	Bal
Max	0.07	1.00	1.00	0.040	0.030	17.50	0.50	5.00	0.45	5.00	–
Typical Mechanical Properties (AMS5643)											

	0.2% Proof Stress	Tensile Strength	Elongation	Reduction of area	Hardness	
	MPA	MPA	%	%	HB	
	Min	Min	Min	Min	Min	Max
			L	L		
<b>H900</b>	1172	1310	10	40	388	444
<b>H925</b>	1069	1172	10	44	375	429
<b>H1025</b>	1000	1069	12	45	331	401
<b>H1075</b>	862	1000	13	45	311	375
<b>H1100</b>	793	965	14	45	302	363
<b>H1150</b>	724	931	16	50	277	352

\* This data has been supplied in good faith and is indicative only. It has been provided for general information purposes only and is not to be relied upon in place of the full specification. Mechanical properties can vary considerably with different supply conditions such as heat treatment or temper and product dimensions.

No liability will be accepted by Dynamic Metals Ltd in respect of any action taken by any third party in reliance of any of the data provided.

The information provided in this datasheet has been taken from multiple recognised sources. No guarantee is given that the information is from the latest issue of these sources and no guarantee is given that the information in the datasheet is accurate or up to date.

Material supplied by Dynamic Metals Ltd may vary significantly from this data but will conform to the relevant and applicable standards. All transactions are subject to Dynamic Metals Ltd latest Terms and Conditions of Sale.

As the products detailed may be used for a wide variety of purposes and as Dynamic Metals Ltd has no control over their use, Dynamic Metals Ltd specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by Dynamic Metals Ltd to any third party is given for that party's assistance only and without liability on the part of Dynamic Metals Ltd.

All transactions are subject to Dynamic Metals Ltd latest Terms and Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available by request or by downloading from our website.

## General Enquiries

T: +44 (0) 1525 217 556 [\(tel:+4401525217556\)](tel:+4401525217556)

E: [sales@dynamicmetalsltd.com](mailto:sales@dynamicmetalsltd.com) [\(mailto:sales@dynamicmetalsltd.com\)](mailto:sales@dynamicmetalsltd.com)



## UK Address:

### Head Office

40 Eden Way  
Chartwell Business Park

Leighton Buzzard  
Bedfordshire  
LU7 4FY

T: +44 (0)1525 217 556 [\\_\(tel:+441525217556\)](tel:+441525217556)

*Conversion Centre*

Suite 2 Meadowhall Riverside  
Meadowhall Road  
Sheffield  
South Yorkshire  
S9 1BW

T: +44 (0)1143 030 320 [\\_\(tel:+4401143030320\)](tel:+4401143030320)

*Registered Office (only)*

The Granary  
Crowhill Farm Ravensden Road  
Wilden  
Bedfordshire  
MK44 2QS

T: +44 (0)1525 217 556 [\\_\(tel:+441525217556\)](tel:+441525217556)



[\(/media/zn2dbklo/cyber-essentials-certified-plus.png\)]((/media/zn2dbklo/cyber-essentials-certified-plus.png))



[\(/media/dyelbliq/cyber-essentials-certified.png\)](#)