

## A286 STAINLESS STEEL BAR - AMS 5726, AMS 5731, AMS 5732

A286 is a precipitation hardenable alloy. High nickel and chromium content gives it a good resistance to corrosion up to about 1300 Deg C and Oxidation up to about 1500 Deg F. A286 (UNS S66286) can be age hardened to a high strength level. The alloy is also used for low temperature applications requiring a ductile, non-magnetic high strength material at temperatures ranging from above room temperature down to at least -320 Deg F. The alloy (AMS 5726, AMS 5731, AMS 5732, AMS 5737) may be used for moderate corrosion applications in aqueous solutions.

Specific Gravity													
7.9 g/cm3													
Typical Applications							Related Specifications						
Fasteners  Stud Bolts  Industrial Gas Turbines							<b>AMS 5726</b>  <b>AMS 5731</b>  <b>AMS 5732</b>  <b>AMS 5737</b>  <b>BS HR 51</b>  <b>BS HR 52</b>  <b>W.Nr 1.4943</b>  <b>W.Nr 1.4944</b>  <b>UNS S66286</b>						
Chemical Composition (Wt %)													
	C	Mn	P	S	Si	Cr	Ni	Mo	Ti	V	Al	B	Fe
Min	-	-	-	-	-	13.5	24	1	1.9	0.10	-	0.003	-
Max	0.08	2.0	0.025	0.025	1	16	27	1.5	2.35	0.50	0.035	0.010	Bal
Typical Mechanical Properties													
					0.2% Proof Stress	Tensile Strength	Elongation	Reduction of area	Hardness				

	MPA	MPA	%	%	HB
	Min	Min	Min	Min	
<b>Sol treated and Aged 1800 Deg F (AMS 5732)</b>	586	896	15	–	248 – 341
<b>Sol Treated and Aged 1650 Deg F (AMS 5737)</b>	655	965	12	–	277 – 363

\* This data has been supplied in good faith and is indicative only. It has been provided for general information purposes only and is not to be relied upon in place of the full specification. Mechanical properties can vary considerably with different supply conditions such as heat treatment or temper and product dimensions.

No liability will be accepted by Dynamic Metals Ltd in respect of any action taken by any third party in reliance of any of the data provided.

The information provided in this datasheet has been taken from multiple recognised sources. No guarantee is given that the information is from the latest issue of these sources and no guarantee is given that the information in the datasheet is accurate or up to date.

Material supplied by Dynamic Metals Ltd may vary significantly from this data but will conform to the relevant and applicable standards. All transactions are subject to Dynamic Metals Ltd latest Terms and Conditions of Sale.

As the products detailed may be used for a wide variety of purposes and as Dynamic Metals Ltd has no control over their use, Dynamic Metals Ltd specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by Dynamic Metals Ltd to any third party is given for that party's assistance only and without liability on the part of Dynamic Metals Ltd.

All transactions are subject to Dynamic Metals Ltd latest Terms and Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions, a copy of which is available by request or by downloading from our website.

## General Enquiries

T: +44 (0) 1525 217 556 [\(tel:+4401525217556\)](tel:+4401525217556)

E: [sales@dynamicmetalsltd.com](mailto:sales@dynamicmetalsltd.com) [\(mailto:sales@dynamicmetalsltd.com\)](mailto:sales@dynamicmetalsltd.com)



## UK Address:

### Head Office

40 Eden Way  
Chartwell Business Park  
Leighton Buzzard  
Bedfordshire  
LU7 4FY

T: +44 (0)1525 217 556 [\(tel:+441525217556\)](tel:+441525217556)

### Conversion Centre

Suite 2 Meadowhall Riverside  
Meadowhall Road  
Sheffield  
South Yorkshire  
S9 1BW

T: +44 (0)1143 030 320 [\(tel:+4401143030320\)](tel:+4401143030320)

Registered Office (only)

The Granary  
Crowhill Farm Ravensden Road  
Wilden  
Bedfordshire  
MK44 2QS

T: +44 (0)1525 217 556 [\\_\(tel:+441525217556\)](tel:+441525217556)



[\(/media/zn2dbklo/cyber-essentials-certified-plus.png\)](/media/zn2dbklo/cyber-essentials-certified-plus.png)



[\(/media/dyelbliq/cyber-essentials-certified.png\)](/media/dyelbliq/cyber-essentials-certified.png)