

AMS 5629 - Ph 13-8MO Stainless Steel

Typical Applications

Fasteners

Valves

Fittings

Petrochemical Components

Aircraft Structural parts



PH 13/8 MO is a precipitation hardening stainless steel alloy that conforms to the AMS 5629, AMS 5864, AMS 5862 specifications.

This material is characterised by excellent strength, corrosion resistance, and toughness at both room and elevated temperatures.

PH 13/8 MO (UNS S13800) is often used in aerospace, chemical processing, and power generation applications where high strength and corrosion resistance are essential. The material is not particularly easy to work with due to its high strength and toughness, which can make cutting and machining difficult. However, with the proper equipment and techniques, it is possible to fabricate and form PH 13/8 MO into complex shapes and components.

It is a medium to high strength material achieved through appropriate ageing treatments (see table below) and contains very good resistance to stress corrosion. PH 13/8MO stainless steel is produced by Vacuum Induction Melting (VIM) followed by Vacuum Arc Remelting (VAR).

Related Products

15 5Ph Stainless Steel

17 4Ph

17 7Ph

431 - 1-4057 STAINLESS STEEL

A286 Bar

A286 Sheet

Aermet 100

Ph 13 8Mo

S145 Stainless Steel

Technical specification

Related Specifications

AMS 5629

AMS 5864

UNS S13800

W.Nr 1.4534

Specific Gravity

7.76 g/cm³

Chemical Composition (WT %)

	Min	Max
C	-	0.05
Si	-	0.10
Mn	-	0.10
P	-	0.01

S	-	0.008
Cr	12.24	13.25
Mo	2.00	2.50
Ni	7.50	8.50
Al	0.90	1.35
N	-	0.010
Fe	Bal	-

Typical Mechanical Properties in the Annealed condition

			H950	H1000	H1025	H1050	H1100	H1150
0.2% Proof Stress	MPA	Min	1413	1310	1207	1138	931	621
Tensile Strength	MPA	Min	1517	1413	1276	1207	1034	931
Elongation	%	Min	10	10	11	12	14	14
Reduction of area	%	Min	45	60	50	50	50	50
Reduction of area	%	Min	35	40	45	45	50	50
Hardness	HRC	Min	45	43	41	40	34	30

The data we have supplied is general and is intended to provide information only and is not intended to be a substitute for professional advice. We do not accept any liability for any loss or damage arising from the use of the information provided. The information is provided for general information only and is not intended to be a substitute for professional advice. We do not accept any liability for any loss or damage arising from the use of the information provided.

Need more information? **Get in touch**

General Enquiries

+44(0) 1525 217 556

Email us here

Head Office

40 Eden Way
Chartwell Business Park
Leighton Buzzard
Bedfordshire
LU7 4FY

T: +44 (0)1525 217 556

Conversion Centre

Suite 2 Meadowhall Riverside
Meadowhall Road
Sheffield
South Yorkshire
S9 1BW

T: +44 (0)1143 030 320

Useful Links

Privacy Policy

Sitemap

