

# AMS 4928, BS TA11, TITANIUM 6AL4V BAR

## BS TA11 TITANIUM 6AL4V BAR

6AL4V, also known as titanium alloy 6-4, is a high-performance material which is known for its exceptional strength to weight ratio, corrosion resistance, and biocompatibility. The typical applications of Titanium 6AL4V are aerospace for structural components, motorsport and medical implants.

At its core, 6AL4V is a titanium alloy, composed of titanium alloyed with 6% aluminium and 4% vanadium, the addition of aluminium enhances the alloy's strength and resistance to creep deformation, while vanadium further bolsters its strength and improves its resistance to corrosion and oxidation.

A notable characteristic of the 6AL4V alloy is its exceptional strength-to-weight ratio. This means that it is particularly well suited for applications where minimizing weight is critical, as is often the case in the aerospace sector. Though relatively lightweight, 6AL4V demonstrates impressive mechanical properties that allow it to endure substantial forces and stresses without any detriment to its structural integrity.

Furthermore, 6AL4V has exceptional corrosion resistance, this characteristic makes it a preferred choice for marine applications, chemical processing equipment, and medical implants, where resistance to bodily fluids and biological environments is essential.

A key attribute of the 6AL4V (AMS 4928) alloy is its notable biocompatibility. When combined with its impressive strength properties and robust corrosion resistance, this biocompatibility makes 6AL4V highly suitable for biomedical applications. As a result, Ti-6Al-4V is used widely in the production of orthopaedic implants, dental implants, and a diverse range of surgical instrumentation.

Specific Gravity	
4.484 g/cm <sup>3</sup>	
Typical Applications	Related Specifications
Medical Implants Turbine Blades Fasteners Motor Racing applications Aircraft Structural Components	<b>AMS 2631C</b> <b>AMS 4928</b> <b>AMS 4965</b> <b>AMS 4967</b> <b>AMS 6931</b> <b>AMS STD 2154</b> <b>AMS T 9047</b> <b>ASTM B348</b> <b>BS TA11</b> <b>TA28</b> <b>ISO 5832-3</b> <b>W.Nr 3.7164/5</b>

**ASTM F136**  
**UNS R56400**  
**MSRR 8652**  
**MSRR 8614**

**Chemical Composition (Wt %)**

	C	Al	N	O	Ti	V	Fe	H	Y
<b>Min</b>	–	5.5	–	–	–	3.50	–	–	–
<b>Max</b>	0.08	6.75	0.05	0.2	Bal	4.50	0.25	0.01	0.005

**Typical Mechanical Properties in the Annealed condition**

<b>0.2% Proof Stress</b>	<b>Tensile Strength</b>	<b>Elongation</b>	<b>Reduction of area</b>	<b>Hardness</b>
MPA	MPA	%	%	HRC
Min	Min	Min	Min	
862	900	10	25	36

\* This data has been supplied in good faith and is indicative only. It has been provided for general information purposes only and is not to be relied upon in place of the full specification. Mechanical properties can vary considerably with different supply conditions such as heat treatment or temper and product dimensions.

No liability will be accepted by Dynamic Metals Ltd in respect of any action taken by any third party in reliance of any of the data provided.

The information provided in this datasheet has been taken from multiple recognised sources. No guarantee is given that the information is from the latest issue of these sources and no guarantee is given that the information in the datasheet is accurate or up to date.

Material supplied by Dynamic Metals Ltd may vary significantly from this data but will conform to the relevant and applicable standards. All transactions are subject to Dynamic Metals Ltd latest Terms and Conditions of Sale.

As the products detailed may be used for a wide variety of purposes and as Dynamic Metals Ltd has no control over their use, Dynamic Metals Ltd specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by Dynamic Metals Ltd to any third party is given for that party's assistance only and without liability on the part of Dynamic Metals Ltd.

All transactions are subject to Dynamic Metals Ltd latest Terms and Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available by request or by downloading from our website.

**General Enquiries**

T: +44 (0) 1525 217 556 [\(tel:+4401525217556\)](tel:+4401525217556)

E: [sales@dynamicmetalsltd.com](mailto:sales@dynamicmetalsltd.com) [\(mailto:sales@dynamicmetalsltd.com\)](mailto:sales@dynamicmetalsltd.com)



**UK Address:**

*Head Office*

40 Eden Way  
Chartwell Business Park  
Leighton Buzzard  
Bedfordshire  
LU7 4FY

T: +44 (0)1525 217 556 [\\_\(tel:+441525217556\)](tel:+441525217556)

*Conversion Centre*

Suite 2 Meadowhall Riverside  
Meadowhall Road  
Sheffield  
South Yorkshire  
S9 1BW

T: +44 (0)1143 030 320 [\\_\(tel:+4401143030320\)](tel:+4401143030320)

*Registered Office (only)*

The Granary  
Crowhill Farm Ravensden Road  
Wilden  
Bedfordshire  
MK44 2QS

T: +44 (0)1525 217 556 [\\_\(tel:+441525217556\)](tel:+441525217556)



[\(/media/zn2dbklo/cyber-essentials-certified-plus.png\)](/media/zn2dbklo/cyber-essentials-certified-plus.png)



[\(/media/dyelbliq/cyber-essentials-certified.png\)](#)