

AMS 4902, TITANIUM GRADE 2 SHEETS AND PLATES

Titanium Grade 2 is a commercially pure form of titanium. It is widely used because it combines excellent formability and moderate strength with superior corrosion resistance. This combination of properties makes Grade 2 titanium (ASTM B265, AMS 4902, UNS R50400) ideal for a large variety of chemical and marine as well as aerospace and medical applications.

Specific Gravity							
4.51 g/cm ³							
Typical Applications				Related Specifications			
Airframe skins Chemical Process vessels Exhausts components Medical and dental implants Sputtering Targets				ASTM B265 ASME SB-265 TA2 AMS 4902 UNS R50400 W.Nr 3.7034 AMS T 9046			
Chemical Composition (Wt %)							
	C	N	O	Ti	Fe	H	Other
Min	–	–	–	–	–	–	–
Max	0.08	0.03	0.250	Bal	0.30	0.015	0.40
Typical Mechanical Properties in the Annealed Condition							
0.2% Proof Stress	Tensile Strength	Elongation	Reduction of area	Hardness			
MPA	MPA	%	%	HRB			
Min	Min	Min					
275	345	20	30	80			

What is AMS 4902?

AMS 4902 is a Titanium Grade 2 sheet and plate variation. This is an aerospace material specification known as AMS 4902. The combination of strength and fatigue resistance of this material makes it popular for use in the aerospace

industry.

Benefits of AMS 4902

AMS 4902 offers several key benefits:

- Has a high strength to weight ratio, good for aircraft structures.
- Fatigue resistance is good, vital in components which are subjected to repeated stress
- Allows for easier fabrication of complex parts that have good machinability
- Enhancing safety in aerospace applications based on superior damage tolerance
- The strict AMS standards offer consistent and reliable performance of all packages.
- Widely available and familiar within the aerospace industry.

Does 4902 rust easily?

AMS 4902 does not rust in the traditional sense as rusting is a term which is specifically used for the corrosion of iron and steel. Although, Titanium variations including AMS 4902 can corrode under certain conditions. Although AMS 4902 has excellent corrosion resistance for many metals, it is not as corrosion resistant as compared to other alloys.

AMS 4902 is susceptible to pitting and intergranular corrosion especially in environments with high chloride content (i.e. marine atmospheres). However, to counter this the material is often treated in other ways such as anodising or alclad coating to give additional corrosion protection in aerospace use.

What Industries Commonly Require AMS 4902?

Common applications

This high-performance Titanium finds use in a wide range of applications, including:

- Aircraft structural components
- Jet engine parts
- Marine propeller shafts
- Chemical processing equipment
- Offshore oil and gas components
- High-performance automotive parts

* This data has been supplied in good faith and is indicative only. It has been provided for general information purposes only and is not to be relied upon in place of the full specification. Mechanical properties can vary considerably with different supply conditions such as heat treatment or temper and product dimensions.

No liability will be accepted by Dynamic Metals Ltd in respect of any action taken by any third party in reliance of any of the data provided.

The information provided in this datasheet has been taken from multiple recognised sources. No guarantee is given that the information is from the latest issue of these sources and no guarantee is given that the information in the datasheet is accurate or up to date.

Material supplied by Dynamic Metals Ltd may vary significantly from this data but will conform to the relevant and applicable standards. All transactions are subject to Dynamic Metals Ltd latest Terms and Conditions of Sale.

As the products detailed may be used for a wide variety of purposes and as Dynamic Metals Ltd has no control over their use, Dynamic Metals Ltd specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by Dynamic Metals Ltd to any third party is given for that party's assistance only and without liability on the part of Dynamic Metals Ltd.

All transactions are subject to Dynamic Metals Ltd latest Terms and Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions, a copy of which is available by request or by downloading from our website.

General Enquiries

T: +44 (0) 1525 217 556 [\(tel:+4401525217556\)](tel:+4401525217556)

E: sales@dynamicmetalsltd.com [\(mailto:sales@dynamicmetalsltd.com\)](mailto:sales@dynamicmetalsltd.com)



UK Address:

Head Office

40 Eden Way
Chartwell Business Park
Leighton Buzzard
Bedfordshire
LU7 4FY

T: +44 (0)1525 217 556 [.\(tel:+441525217556\)](tel:+441525217556)

Conversion Centre

Suite 2 Meadowhall Riverside
Meadowhall Road
Sheffield
South Yorkshire
S9 1BW

T: +44 (0)1143 030 320 [.\(tel:+4401143030320\)](tel:+4401143030320)

Registered Office (only)

The Granary
Crowhill Farm Ravensden Road
Wilden
Bedfordshire
MK44 2QS

T: +44 (0)1525 217 556 [.\(tel:+441525217556\)](tel:+441525217556)



[\(/media/zn2dbklo/cyber-essentials-certified-plus.png\)]((/media/zn2dbklo/cyber-essentials-certified-plus.png))



[\(/media/dyelbliq/cyber-essentials-certified.png\)](#)