

TITANE GRADE 2 BARRES

Le grade 2 est une forme de Titane commercial Pur. C'est utilisé très couramment car il combine une excellente formabilité, une résistance modérée ainsi qu'une haute résistance à la corrosion. Cette combinaison de propriétés rend le grade 2 idéal pour une large gamme d'applications pour la chimie, la marines et aérospatiales.

Specific Gravity							
4.51 g/cm3							
Typical Applications				Related Specifications			
Acetabular cups				ASTM B348			
Brackets				ASTM F67			
Condensors				AMS T 9047			
Cryogenic vessels				NACE MR01-75			
Jigs				UNS R50400			
Cathodes				W.Nr 3.7034			
Chemical Composition (Wt %)							
	C	N	O	Ti	Fe	H	Other
Min	—	—	—	—	—	—	—
Max	0.08	0.03	0.250	Bal	0.30	0.015	0.40
Typical Mechanical Properties in the Annealed condition							
0.2% Proof Stress	Tensile Strength	Elongation	Reduction of area	Hardness			
MPA	MPA	%	%	HRB			
Min	Min	Min					
275	345	20	30	80			
* Every effort has been made to ensure that our technical specifications are accurate. However, technical specifications included within Dynamic Metals Ltd should be used as a guideline only and are subject to change without notice.							

General Enquiries

T: +44 (0) 1525 217 556 [\(tel:+4401525217556\)](tel:+4401525217556)

E: sales@dynamicmetalsltd.com [\(mailto:sales@dynamicmetalsltd.com\)](mailto:sales@dynamicmetalsltd.com)



UK Address:

Head Office

40 Eden Way
Chartwell Business Park
Leighton Buzzard
Bedfordshire
LU7 4FY

T: +44 (0)1525 217 556 [\(tel:+441525217556\)](tel:+441525217556)

Conversion Centre

Suite 2 Meadowhall Riverside
Meadowhall Road
Sheffield
South Yorkshire
S9 1BW

T: +44 (0)1143 030 320 [\(tel:+4401143030320\)](tel:+4401143030320)

Registered Office (only)

The Granary
Crowhill Farm Ravensden Road
Wilden
Bedfordshire
MK44 2QS

T: +44 (0)1525 217 556 [\(tel:+441525217556\)](tel:+441525217556)



[\(/media/zn2dbklo/cyber-essentials-certified-plus.png\)](#)



[\(/media/dyelbliq/cyber-essentials-certified.png\)](#)