

## 2618 ALUMINIUM - UNS A92618

2618 is an aluminium copper alloy with high strength and heat resistance, its composition also includes magnesium and iron, which contribute to its performance. Its typical use is in aerospace for pistons and rotating aircraft parts and automotive pistons due to its ability to maintain strength at elevated temperatures.

2618 has good resistance to fatigue, this means that 2618 is suited well for components subjected to cyclic stress, this characteristic is particularly valuable in high-stress applications requiring long-term reliability, such as aircraft engine parts. Engineers often select 2618 for components that must withstand prolonged stress periods due to its resilience under repeated loading.

In terms of workability, 2618 offers reasonable machinability, allowing for the production of complex shapes. Welding 2618 presents more challenges than some other aluminium alloys, it demands specific techniques and a higher level of expertise to achieve reliable joints.

While 2618 provides adequate corrosion resistance for many applications, it's not amongst the top performers in this area. If used in particularly corrosive environments, additional protective measures may be necessary to ensure longevity.

The alloy's strength-to-weight ratio is favourable, though not exceptional within the spectrum of high-performance aluminium alloys, this balance of properties makes it a practical choice for applications where both weight and strength are important considerations.

Heat treatment can significantly influence the mechanical properties of 2618, these processes are crucial to achieve optimal strength and performance characteristics.

It's worth noting that 2618 may not be the best choice for applications requiring high ductility or formability, its strength comes at the cost of some malleability, which can limit its use in certain manufacturing processes.

<b>Density</b>											
2.75g/cm <sup>3</sup>											
<b>Typical Applications</b>						<b>Related Specifications</b>					
Aerospace & Defence Commonly used for pistons and rotating aircraft components due to its high strength at elevated temperatures						UNS A92618 EN 573 EN AW-2618 BS H16 A-U2GN					
<b>Chemical Composition (Wt %)</b>											
	Al	Si	Fe	Cu	Mn	Mg	Ni	Zn	Ti	Zr+Ti	Pb+Sn
<b>Min</b>	<b>Bal</b>	-	0.90	1.80	-	1.20	0.80	-	-	-	-

<b>Max</b>	<b>Bal</b>	0.25	1.4	2.70	0.20	1.80	1.40	0.10	0.20	0.25	0.05
------------	------------	------	-----	------	------	------	------	------	------	------	------

### Typical Mechanical Properties

	0.2% Proof Stress	Tensile Strength	Elongation	Reduction of area	Typical Hardness (HBW)
<b>Content</b>	340	420	7	-	-

### Hardness after Heat Treatment

\* This data has been supplied in good faith and is indicative only. It has been provided for general information purposes only and is not to be relied upon in place of the full specification. Mechanical properties can vary considerably with different supply conditions such as heat treatment or temper and product dimensions.

No liability will be accepted by Dynamic Metals Ltd in respect of any action taken by any third party in reliance of any of the data provided.

The information provided in this datasheet has been taken from multiple recognised sources. No guarantee is given that the information is from the latest issue of these sources and no guarantee is given that the information in the datasheet is accurate or up to date.

Material supplied by Dynamic Metals Ltd may vary significantly from this data but will conform to the relevant and applicable standards. All transactions are subject to Dynamic Metals Ltd latest Terms and Conditions of Sale.

As the products detailed may be used for a wide variety of purposes and as Dynamic Metals Ltd has no control over their use, Dynamic Metals Ltd specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by Dynamic Metals Ltd to any third party is given for that party's assistance only and without liability on the part of Dynamic Metals Ltd.

All transactions are subject to Dynamic Metals Ltd latest Terms and Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions, a copy of which is available by request or by downloading from our website.

## General Enquiries

T: +44 (0) 1525 217 556 [\(tel:+4401525217556\)](tel:+4401525217556)

E: [sales@dynamicmetalsltd.com](mailto:sales@dynamicmetalsltd.com) [\(mailto:sales@dynamicmetalsltd.com\)](mailto:sales@dynamicmetalsltd.com)



## UK Address:

### Head Office

40 Eden Way  
 Chartwell Business Park  
 Leighton Buzzard  
 Bedfordshire  
 LU7 4FY

T: +44 (0)1525 217 556 [\(tel:+441525217556\)](tel:+441525217556)

*Conversion Centre*


Suite 2 Meadowhall Riverside  
Meadowhall Road  
Sheffield  
South Yorkshire  
S9 1BW

T: +44 (0)1143 030 320 [\\_\(tel:+4401143030320\)](tel:+4401143030320)

*Registered Office (only)*

The Granary  
Crowhill Farm Ravensden Road  
Wilden  
Bedfordshire  
MK44 2QS

T: +44 (0)1525 217 556 [\\_\(tel:+441525217556\)](tel:+441525217556)



[\(/media/zn2dbklo/cyber-essentials-certified-plus.png\)](#)



[\(/media/dyelbliq/cyber-essentials-certified.png\)](#)