

AMS 5660, AMS 5661, NICKEL ALLOY 901

Nickel Alloy 901 (AMS 5660, AMS 5661, BS HR55) is a nickel-based alloy offering high strength and outstanding resistance to corrosion and oxidation at extreme temperatures. Primarily composed of nickel, along with substantial amounts of chromium and smaller additions of iron and silicon, this alloy is exceptionally versatile for demanding industrial applications.

Its standout quality is retaining high strength and stability in temperatures up to 600°C. This allows Nickel Alloy 901 to withstand incredibly hot and arduous environments that would cause most other metals to fail or rapidly degrade. Components made from this alloy maintain their integrity despite continuous exposure to hot gases, combustion products or thermal cycling.

This capability stems from the carefully balanced composition of Nickel Alloy 901. The high nickel content coupled with generous chromium provides a protective chromium oxide layer on the metal's surface when heated, shielding it from oxidation damage. The addition of silicon enhances this protective effect and the iron helps fine-tune the physical properties of the alloy. Combined, these elements allow Nickel Alloy 901 products to continuously perform in the hottest sections of industrial plants, power generation equipment and vehicle engines.

Potential applications that could benefit from Nickel Alloy 901's thermal and corrosion resistance include furnace components, parts for aircraft and land-based gas turbines, rocket engine nozzles, nuclear power systems, heat exchangers and any component facing extremely high heat.

Specific Gravity												
8.14 g/cm3												
Typical Applications								Related Specifications				
Aircraft Rocket Engines Gas Turbine Components Furnace Components								AMS 5660				
								AMS 5661				
								BS HR55				
								US NO9901				
Chemical Composition (Wt %)												
	Ni	Cr	Si	S	Co	FE	Al	C	Mn	Mo	Ti	Cu
Min	40	11	-	-	-	Bal	-	-	-	5	2.8	-
Max	45	14	0.4	0.03	1		0.35	0.1	0.5	6.5	3.1	0.5

**Typical Mechanical Properties
(in the solution treated condition)**

0.2% Proof Stress			Tensile Strength			Elongation			Reduction		
MPA			MPA			%			%		
862			1207			15			19		

What is Alloy 901?

Alloy 901 is a nickel-based alloy, that offers high strength and resistance to corrosion and oxidation at high temperatures. Typical applications are Aircraft parts, rocket engines, gas turbine components and furnace components.

What is the composition of Alloy 901?

Alloy 901 is mainly nickel, iron and chromium, which also contains Titanium and Aluminium for precipitation hardening and molybdenum for strength.

What are the typical uses for Alloy 901?

Typical uses include Aircraft parts, Rocket Engines, Gas Turbine Components, Furnace Components. Alloy 901 is mainly used for components facing extremely high heat.

* This data has been supplied in good faith and is indicative only. It has been provided for general information purposes only and is not to be relied upon in place of the full specification. Mechanical properties can vary considerably with different supply conditions such as heat treatment or temper and product dimensions.

No liability will be accepted by Dynamic Metals Ltd in respect of any action taken by any third party in reliance of any of the data provided.

The information provided in this datasheet has been taken from multiple recognised sources. No guarantee is given that the information is from the latest issue of these sources and no guarantee is given that the information in the datasheet is accurate or up to date.

Material supplied by Dynamic Metals Ltd may vary significantly from this data but will conform to the relevant and applicable standards. All transactions are subject to Dynamic Metals Ltd latest Terms and Conditions of Sale.

As the products detailed may be used for a wide variety of purposes and as Dynamic Metals Ltd has no control over their use, Dynamic Metals Ltd specifically excludes all conditions or warranties expressed or implied by statute or otherwise as to dimensions, properties and/or fitness for any particular purpose, whether expressed or implied.

Advice given by Dynamic Metals Ltd to any third party is given for that party's assistance only and without liability on the part of Dynamic Metals Ltd.

All transactions are subject to Dynamic Metals Ltd latest Terms and Conditions of Sale. The extent of the Company's liabilities to any customer is clearly set out in those Conditions; a copy of which is available by request or by downloading from our website.

General Enquiries

T: +44 (0) 1525 217 556 [\(tel:+4401525217556\)](tel:+4401525217556)

E: sales@dynamicmetalsltd.com [\(mailto:sales@dynamicmetalsltd.com\)](mailto:sales@dynamicmetalsltd.com)



UK Address:

Head Office

40 Eden Way
Chartwell Business Park
Leighton Buzzard
Bedfordshire
LU7 4FY

T: +44 (0)1525 217 556 [_\(tel:+441525217556\)](tel:+441525217556)

Conversion Centre


Suite 2 Meadowhall Riverside
Meadowhall Road
Sheffield
South Yorkshire
S9 1BW

T: +44 (0)1143 030 320 [_\(tel:+4401143030320\)](tel:+4401143030320)

Registered Office (only)

The Granary
Crowhill Farm Ravensden Road
Wilden
Bedfordshire
MK44 2QS

T: +44 (0)1525 217 556 [_\(tel:+441525217556\)](tel:+441525217556)



[\(/media/zn2dbklo/cyber-essentials-certified-plus.png\)](/media/zn2dbklo/cyber-essentials-certified-plus.png)



[\(/media/dyelbliq/cyber-essentials-certified.png\)](#)